



ARDEX K 15

Self-Levelling Sub-Floor Smoothing Compound

Rapid hardening – walkable in approximately 2 hours

Rapid drying - receives floorcovering within 24 hours regardless of thickness

Can be applied by trowel or pump

Strong – high compressive strength

Suitable for floors with underfloor heating

Ideal for use with ARDEX floorcovering adhesives

Rapid dry formula

Certified for marine installation with MED-B & D certs

RAPIDRY



FORMULA

What is the Rapidry Formula?

Binds the mix water within the mortar, speeding drying and hardening times irrespective of application thickness



ARDEX-QUICSEAL SINGAPORE PTE. LTD.

26 Tuas Ave 4 Singapore 639376

Telephone: +65 6861 7700

Fax: +65 6741 4666

Email: sales@ardex-quickseal.com

Website: www.ardex-quickseal.com

ARDEX K 15

Self-Levelling Sub-Floor Smoothing Compound

DESCRIPTION

ARDEX K 15 is an advanced sub-floor smoothing compound. It is virtually tension free and is designed to rapidly level and smooth hard sub-floors prior to applying a floor finish. Used in conjunction with either ARDEX P 82 or ARDEX P 51 primers, ARDEX K 15 can be applied to old sub-floors, e.g. floor screeds and other hard and rigid bases. ARDEX K 15 is a grey powder consisting of special cements and high quality synthetic resins. When mixed with water, a fluid, self-levelling mortar is produced which can be applied from a feather edge up to the required thickness in one operation. For thicknesses greater than 10 mm, incorporate ARDEX Aggregate in the mixed mortar. ARDEX K 15 can normally be walked on after approximately 2 hours at 20°C and dries and hardens rapidly so that even thick applications are ready to receive floorcoverings within one day at 20°C.

USE

ARDEX K 15 will level and smooth, in a single application, internal sub-floors of concrete, cement/sand screeds, quarry tiles, etc., prior to the installation of floorcoverings. Applications include smoothing tamped, uneven, damaged or rained-on in situ concrete sub-floors, adjusting tolerances or camber problems between floors, slabs or pre-cast concrete as well as smoothing old sub-floors and screeds in renovation projects. ARDEX K 15 is especially useful where the installation time of the floorfinish must be kept to a minimum.

SUBSTRATE PREPARATION

The surface must be hard, sound and free of dust, dirt and other barrier materials such as paint, lime coatings, plaster and excessive adhesive residues etc. Use ARDEX DGR degreaser to remove polish, wax, grease, oil and similar contaminating substances. Laitance should be removed from concrete surfaces. Direct to earth sub-floors must have an effective dampproof membrane, such as ARDEX DPM. Contact our Technical Services Department for further information.

ALL SURFACES MUST BE PRIMED. ARDEX P 82 primer is recommended for use on smooth, non-absorbent sub-floors. e.g. power coated concrete, smooth pre-cast concrete, asphalt and sound

terrazzo, ceramic or quarry tile flooring. ARDEX P 82 primer should also be used on impervious sub-floors which have traces of sound adhesive residues. ARDEX P 51 primer should be used on porous or rough surfaces, e.g. cement and sand screeds, scabbled concrete etc. See Priming and Preparation Leaflet for correct dilution rates. Where porous and absorbent sub-floors, e.g. cement and sand screeds, have traces of sound adhesive residues use ARDEX P 51 primer diluted with an equal volume of water.

MIXING

To the required amount of clean water in a clean mixing container add the powder whilst stirring thoroughly until a lump free mortar is produced. The mixing proportions by volume are approximately:- 5.5–6 litres of clean water per 25 kg bag of ARDEX K 15. Use the minimum amount of water for thick applications or cold conditions.

The use of an ARDEX mixing paddle with a 10 mm chuck slow speed (600–1,000 r.p.m.) electric drill makes light work of mixing. Mixed ARDEX K 15 should be applied within 30 minutes at 20°C. This time is extended at lower and reduced at higher temperatures.

APPLICATION

Pour the mixed ARDEX K 15 onto the prepared sub-floor. The mixed mortar will flow out and self-level above 3 mm during the first 15 minutes of its 30 minutes working time. Use a suitable spreader to obtain the required thickness. A long handled ARDEX gauging tool with height adjustment for thickness will simplify this operation. A long handled ARDEX smoothing trowel can be used for finishing off. A steel finishing float can be used for feather edging and touch up work. See the ARDEX tool catalogue for details. Apply at temperatures above 5°C.

THICKNESS

ARDEX K 15 should be applied at thicknesses greater than 3 mm to benefit from its self-levelling properties.

NOTE: Non-absorbent sub-floors, e.g. flooring grade asphalt, must be levelled with at least 3 mm of the smoothing compound.

ARDEX K 15

Self-Levelling Sub-Floor Smoothing Compound

NOTE: No more than 6 mm of ARDEX K 15 should be used on top of asphalt.

When applying ARDEX K 15 at thicknesses of over 10 mm, incorporate up to an equal volume of 3 mm single sized chippings. For thicknesses exceeding 20 mm up to 35 mm, up to an equal volume of 3–8 mm aggregate may be used.

Mix the ARDEX K 15 as above and add the aggregate without further addition of water.

For thicknesses greater than 7 mm up to 35 mm thick it is preferable, more convenient, as well as economical to use ARDEX K 15-B (Base coat) and subsequently apply a 3 mm smoothing layer of ARDEX K 15.

NOTE: It is recommended that the floorcovering is applied within 24 hours, however, where the applied mortar is subjected to rapid drying conditions e.g. direct sunlight, through draughts or where the installation of the floorcovering is delayed for longer than 24 hours, the surface should be covered until the floorcovering is laid.

SPECIFIC APPLICATIONS

When applying ARDEX K 15 either over grade asphalt, or over with traces of sound, hard, non-water softenable adhesive residues, or where a paint or paint thickness coating is to be subsequently applied, ARDEX E 25 must be incorporated in the ARDEX K 15. Consult our Technical Services Department for advice on dilution and incorporation of the ARDEX E 25 mortar admix.

NOTE: That where a paint or paint thickness coating is subsequently applied, the paint or coating used should be checked for suitability and compatibility with ARDEX K 15/ARDEX E 25 before work commences.

Where large-sub-floors require levelling with ARDEX K 15. It may be advantageous to use a pump to mix and place the ARDEX K 15 mortar. Consult our Technical Services Department for advice on this type of application.

COVERAGE

Approximately 1.5 kg ARDEX K 15 powder/m²/mm, e.g. one bag will cover approximately 5 m² at 3 mm thickness.

NOTE:

additional material should be allowed for where the surface is rough or uneven.

PACKAGING

ARDEX K 15 is packed in paper sack incorporating a polyethylene liner - net weight 25 kg.

STORAGE

ARDEX K 15 must be stored in unopened packaging, clear of the ground in cool dry conditions and be protected from excessive draught. If stored correctly, as detailed above, the shelf life of this product is 6 months from the date shown on the packaging.

TECHNICAL DATA

Bulk density of powder	approx. 1.1 kg/litre
Weight of fresh mortar	approx. 1.9 kg/litre
Working time at 20°C	approx. 30 minutes
Flow life at 20°C	approx. 15 minutes
Initial Set (Vicat)	approx. 30 minutes
Final Set (Vicat)	approx. 2 hours
Compressive Strength (DIN 1164)	
After 1 days	18.5 N/mm ²
After 3 days	21.8 N/mm ²
After 7 days	24.8 N/mm ²
After 28 days	28.8 N/mm ²
Tensile Bonding Strength (DIN 1164)	
After 1 days	5.4 N/mm ²
After 3 days	5.8 N/mm ²
After 7 days	6.0 N/mm ²
After 28 days	7.0 N/mm ²
Ball Pressure Hardness (Brinell)	
After 1 days	56.0 N/mm ²
After 3 days	68.0 N/mm ²
After 7 days	72.0 N/mm ²
After 28 days	73.0 N/mm ²
Suitable for underfloor heating	Yes

ARDEX K 15

Self-Levelling Sub-Floor Smoothing Compound

SAFETY PRECAUTIONS

ARDEX K 15 is considered non-hazardous in normal usage. The presence of cement in the product gives an alkaline mortar which may cause some local irritation if prolonged contact with the skin takes place. Care should be taken to avoid inhalation or ingestion of dust and prevent contact with the eyes.

For further information, consult the relevant Safety Data Sheet (SDS) available upon request and online at www.ardex-quicseal.com

DISCLAIMER

The technical datasheets are based on the latest information and given in good faith and represent the best of our knowledge and experience at the time of printing. They are primarily offered for user's consideration and evaluation. It is the responsibility of the user to conduct their own tests to validate the suitability of the products. It is also the responsibility of the user to ensure that the products are used and handled correctly and in accordance with any applicable standards, the product instructions and recommendations and only for the uses they are intended. As we have no control over site conditions and the execution of the work, we accept no liability for any loss or damage which may rise as a result thereof. We also reserve the right to update the information at any time without prior notice to you to reflect our ongoing research and development program.

Vietnam:

Mobile: +84 901 351 308

Email: sales@ardex-quicseal.com

DEC 2022

Offices:

Malaysia:

ARDEX QUICSEAL MALAYSIA SDN. BHD.
No. 35-1, Jalan Puteri 2/3, Bandar Puteri,
47100, Puchong, Selangor Darul Ehsan
Telephone: +603 8069 1139
Telefax: +603 8052 3223
Email: sales@ardex-quicseal.com

Thailand:

ARDEX (THAILAND) CO., LTD
969 2nd Floor, Moo 13, Soi 45, Bangna-Trad Road
Bangkaew, Bangplee, Samutprakarn 10540 Thailand
Telephone: +66 2316 3069 Fax: +66 2316 3075
Email: sales@ardex.co.th
Website: www.ardex.co.th