



ARDEX WPM 300

(HydrEpoxy 300) Water Based Epoxy Moisture Barrier

Water resistant, prevents rising damp and efflorescence

Withstands hydrostatic pressure

Excellent adhesion to most substrates including damp surfaces and freshly laid green concrete

Safe to use in sensitive locations

Green Label certified



ARDEX-QUICSEAL SINGAPORE PTE. LTD.

26 Tuas Ave 4 Singapore 639376

Telephone: +65 6861 7700

Fax: +65 6741 4666

Email: sales@ardex-quickseal.com

Website: www.ardex-quickseal.com

ARDEX WPM 300

(HydrEpoxy 300) Water Based Epoxy Moisture Barrier

DESCRIPTION

ARDEX WPM 300 (HydrEpoxy 300) is a two-component water-based epoxy polyamide membrane/barrier coating.

Approved for the use with potable (drinking) water and independent testing confirms conformity with the requirements of AS4020 and SS375.

FEATURES & BENEFITS

- Non-flammable and negligible odour
- Can be applied to damp surfaces
- Can be safely applied to freshly laid hardened (green) concrete
- Conforms to requirements of the Building Code of Australia as a waterproofing membrane
- When applied directly to the substrate, the cured membrane will withstand 250kPa of hydrostatic pressure which is equivalent to 25 metres head of water
- Can be overcoated using almost any decorative or industrial finishing paint
- Prevents the formation of efflorescence when used as a single barrier coat
- Has excellent adhesion to most substrates including brick, masonry, concrete block, concrete, stone and timber
- Easy to clean-up, using water only

TYPICAL APPLICATIONS

- As a low water vapour transmission coating in the building and construction industries and as a barrier/seal coating over freshly laid or damp concrete
- As a hydrostatic pressure resistant waterproofing membrane to prevent water seepage or dampness penetration through to the interior of walls and floors
- As a waterproofing barrier on the negative side in below grade surfaces such as basements, tunnels, liftwells, retaining walls and carparks
- As a waterproofing membrane or barrier coating over freshly laid hardened (green) concrete, prior to the application of conventional levelling compounds, carpet and tile adhesives
- As a waterproofing membrane in tanking applications, including potable water containment

- As a barrier seal coating over damp, green or efflorescence producing concrete prior to overcoating with conventional building paints

LIMITATIONS

Tiling can commence after 24 hours curing time of ARDEX WPM 300, although it should not exceed a maximum of five days. The installer has to ensure that there is no surface contamination during this period.

The product should be applied whilst the surface temperature is between 10 – 35°C. The product will also be adversely affected in situations where relative humidity is > 85%.

In closed areas, ventilation must be provided during curing cycle to enable adequate evaporation of the water.

Care should be taken when sandwiching adhesives between ARDEX WPM 300 and floor coverings to ensure the water vapour transmission of the covering is sufficient to allow the solvent to escape.

ARDEX WPM 300 is not classified as a trafficable membrane.

SURFACE PREPARATION

All surfaces should be structurally sound and existing coatings, adhesives, efflorescence should be removed to achieve maximum bonding strength and resistance to hydrostatic pressure.

Surfaces must be cleaned, free of dirt, grease, oil or other surface contaminants.

Holes, non-structural cracks or other surface deformities should be filled with ARDEX A 46 mortar or ARDEX concrete repair systems and allowed to cure for 2-3 hours before coating is applied.

INSTALLATION

Each component should be individually mixed to form a homogenous component.

Thoroughly mix the two components in the ratio of 1 : 1 by volume until a blend is obtained. Only mix as much as may be used within the pot life and avoid excessive aeration during mixing. When the product is to be applied to dry concrete, it is advisable to prime

ARDEX WPM 300

(HydrEpoxy 300) Water Based Epoxy Moisture Barrier

with diluted ARDEX WPM 256 at a ratio of 1 : 1 : 1 (1L of water : 1L of part A : 1L of part B) before application and allow it to be touch dry before applying ARDEX WPM 300. The touch dry time of diluted ARDEX WPM 256 should not be more than 2 hours.

Floors: Spread the material using a squeegee or stiff nylon broom to achieve coverage and finish using a long nap roller.

Walls: Apply the product by roller or spray taking care to achieve required coverage.

Care must be taken to work the material into the surface to fill voids and avoid pinholing. A minimum of one coat for efflorescence and green concrete, two coats for waterproofing negative side walls is recommended and care should be taken to ensure uniformity of material and the required coverage is maintained. When finishing, it is necessary to lay the material onto the surface and lightly finish to achieve the required dry film thickness per coat. Minimum 2 coats are required.

The final coverage rate for all surfaces should be a total of 1.5 m² per litre (3 sqm per L wet applied per coat) to achieve optimum properties. In the event that this coverage rate is not achieved in two coats, further coats should be applied to achieve a total uniform coverage rate of 1.5m² per litre; i.e. 300 micrometer dry film thickness.

Allow to cure for 24 hours before applying water-based adhesives, mortars, levelling compounds, decorative coatings or other surface treatments.

Care is necessary to ensure the waterproofing membrane coating is not damaged in any way during subsequent treatments.

TILING APPLICATIONS

Substrates such as screeds and renders should be normally allowed to dry for 7 days prior to the fixing of ceramic tiles. Alternatively, ARDEX WPM 300 can be applied in one coat by brush or roller application at a coverage rate of 3m²/L.

Whilst the coat is wet, clean dry sand of 0.5mm diameter shall be broadcast over the surface at a rate of 700g/m² to achieve at least 90% coverage.

After overnight cure, the excess sand shall be swept

and vacuumed from the surface.

FLOORING APPLICATIONS

Where concrete subfloors are damp, ARDEX WPM 300 can be applied as a moisture barrier. Two coats are applied at 3m² per litre per coat. The second coat can be sand seeded as is done for tile applications or left neat and ARDEX P 82 primer applied before the smoothing cement.

A single coat of ARDEX WPM 300 applied at 2.5m² per litre per coat acts as a moisture stop for green concrete not subject to rising damp or permanent moisture.

PACKAGING

20L /set

PART A: 10L pail

PART B: 10L pail

STORAGE & SHELF LIFE

ARDEX WPM 300 has to be stored in dry, cool condition. With unopened packaging, the product has a shelf life of 12 months.

TECHNICAL PROPERTIES

Colour	Grey
Finish	Semi-gloss going to matt with aging
Mixing ratio	1 : 1 (Part A / Part B) by volume
Coverage	must be applied at a rate of 1.5m ² per litre (3m ² /L per coat) and minimum two coats are required to achieve an effective waterproofing membrane
Dry film thickness	150 micrometers per coat. 300 micrometers minimum with two coats application
Recoat time	4 hours @ 25°C and 50% RH
Pot Life	2 hours @ 25°C 1 hour @ 35°C
VOC content	26g / L

ARDEX WPM 300

(HydrEpoxy 300) Water Based Epoxy Moisture Barrier

The recommended wet film thickness specified produces a nominal dry film thickness of 150 micrometers (0.15mm) per coat. 300 micrometers (0.3mm) for two coats. The apparent dry film thickness will reduce depending on the porosity of the substrate, however the product absorbed by the substrate forms part of the waterproofing function.

THINNING AND CLEAN UP

The first coat should be thinned with water as required depending on the porosity of the surface to be coated (up to 20% for dense surface to 5% for more porous surfaces) to ensure optimum penetration. Thinning of the first and second coat is not allowed since this increases the difficulty in achieving the required dry film thickness. Wash all equipment in water or water/detergent immediately on completion.

SAFETY PRECAUTIONS

ARDEX WPM 300 is hazardous and may cause sensitisation by skin contact. Keep containers in a well ventilated place and tightly closed. Take off immediately all contaminated clothing. In case of eye contact, rinse with plenty of water and contact a doctor. If swallowed, immediately contact doctor or poisons information centre. Avoid release to the environment. Additional information is in the material Safety Datasheet (SDS) available upon request or online at www.ardex-quicseal.com.

DISCLAIMER

The technical datasheets are based on the latest information and given in good faith and represent the best of our knowledge and experience at the time of printing. They are primarily offered for user's consideration and evaluation. It is the responsibility of the user to conduct their own tests to validate the suitability of the products. It is also the responsibility of the user to ensure that the products are used and handled correctly and in accordance with any applicable standards, the product instructions and recommendations and only for the uses they are intended. As we have no control over site conditions and the execution of the work, we accept no liability for any loss or damage which may rise as a result thereof. We also reserve the right to update the information at any time without prior notice to you to reflect our ongoing research and development program.

Offices:

Malaysia:

ARDEX QUICSEAL MALAYSIA SDN. BHD.
72-2, Jalan Puteri 2/2 Bandar Puteri 47100,
Puchong, Selangor Darul Ehsan
Malaysia
Phone: +603 8051 0311
Email: sales.malaysia@ardex-quicseal.com

Thailand:

ARDEX (THAILAND) CO., LTD
969 2nd Floor, Moo 13, Soi 45, Bangna-Trad Road
Bangkaew, Bangplee, Samutprakarn 10540 Thailand
Telephone: +66 2316 3069 Fax: +66 2316 3075
Email: sales@ardex.co.th
Website: www.ardex.co.th

Vietnam:

Mobile: +84 901 351 308
Email: sales@ardex-quicseal.com

July 2024 T