QUICSEAL 718

Fibremesh

Easy to use and handle

Economical

Good wetting properties

Improves tensile strength of liquid applied waterproofing membrane

ARDEX-QUICSEAL SINGAPORE PTE. LTD.
26 Tuas Ave 4 Singapore 639376
Telephone: +65 6861 7700
Fax: +65 6741 4666
Email: sales@ardex-quicseal.com
Website: www.ardex-quicseal.com

QUICSEAL 718

Fibremesh

DESCRIPTION
QUICSEAL 718 Fibremesh is a fibre reinforcing mesh for incorporation into a wide range of liquid applied waterproofing membranes.

USES
- As a reinforcement to a wide range of protective coatings, including modified bitumens, acrylics, polyurethane membranes & flexible cementitious membrane for roofing, pipe wrapping and tank lining, etc.
- Ideal for use in building up required thickness for coatings.

SUBSTRATE PREPARATION
Clean off all moss, dirt and loose material. Ensure that surfaces to be coated are free from contamination ie,. Oil, grease and loose particles, decayed matter, moss and algae growth.

This is best achieved by water-jetting, scrubbing or other approved mechanical means. Where moss or other growths have occurred, treatment with suitable chemicals should be carried out after the initial cleaning process followed by further washing to flush away the chemicals.

APPLICATION
Prime the surface to be reinforced with an appropriate primer or base coat. Allow to dry. Apply a layer of the chosen protective coating by brush or spray over the clean surface of the structure being treated. Immediately, unroll the woven polyester fabric over the coated surface and thoroughly embed with a brush or squeegee. Upon drying, apply second or subsequent coats till the required thickness is achieved.

Provide a minimum of 75mm and 100mm end and side lapping respectively. It is important that the woven polyester fabric is adequately smoothened across the surface to avoid any wrinkling effect. Pipes are usually spirally wrapped by hand or machine with adequate overlap, using a narrow strip of fabric that has been slit to the required width.

TECHNICAL DATA

Colour	White
Weave	Plain
Finished weight	45gm/m^2
Elongation	> 2.5%

SAFE HANDLING PRECAUTIONS
Flammability: Non-flammable
Skin contact: Does not have any effect on sensitive skin.

STORAGE
QUICSEAL 718 Fibremesh must be stored in original packaging, away from sources of ignition and away from direct sunlight.

PACKING
QUICSEAL 718 Fibremesh is available in 1x 50 metre rolls.

IMPORTANT NOTES
The information set forth herein is furnished free of charge in good faith and is based on technical data that QUICSEAL considers to be reliable. This information is intended for used by persons having technical skill and at their own discretion and risk. Information contained in this product sheet conforms to the standard detail recommendations and specifications for the installation of QUICSEAL products as of the date of publication of this document. QUICSEAL makes no other warranties and assumes no liability, expressed or implied, as to the architecture, engineering or workmanship of any project. To ensure that you are using the latest, most complete information, please contact ARDEX-QUICSEAL.

Offices:

Malaysia:
ARDEX QUICSEAL MALAYSIA SDN. BHD.
72-2, Jalan Puteri 2/2 Bandar Puteri 47100,
Puchong, Selangor Darul Ehsan
Malaysia
Phone: +603 8051 0311
Email: sales.malaysia@ardex-quicseal.com

QUICSEAL 718

Fibremesh

Thailand:
ARDEX (THAILAND) CO., LTD
969 2nd Floor, Moo 13, Soi 45, Bangna-Trad Road
Bangkaew, Bangplee, Samutprakarn 10540 Thailand
Telephone: +66 2316 3069 Fax:+66 2316 3075
Email: sales@ardex.co.th
Website: www.ardex.co.th

Vietnam:
Mobile: +84 901 351 308
Email: sales@ardex-quicseal.com

Reference No.: QS 718/210520 T